


Protekt® HD Datasheet

Madico's Classic Fluoropolymer Coating Backsheet Design

MATERIAL COMPOSITION

TEST:	RESULTS:
Thickness*	249 µm
Width Range	51 - 1700 mm
Weight	279 g/m ²
Density	1.15 g/cm ³
Coating Color (air side)	White, Charcoal
EVA Color Options (cell side)	All Colors

FLUOROPOLYMER COATING / PET / EVA



TECHNICAL CHARACTERISTICS

TEST:	TEST SPECIFICATION(S):	RESULTS:
Tensile Strength at Break (MD/TD)	Internal Testing – Data Available	100 MPa (MD) / 112 MPa (TD)
Elongation at Break (MD/TD)	Internal Testing – Data Available	120% (MD) / 110% (TD)
Dimensional Stability	150°C for 30 min; Internal Testing – Data Available	≤ 1%
EVA Peel Strength from Encapsulant	Internal Testing – Data Available	≥ 40 N/cm
Peel Strength of Layers	PET / EVA	≥ 5 N/cm
Relative Thermal Index (RTI)	Suitable for continuous use at 85°C	105°C

ELECTRICAL INSULATION TESTING PERFORMANCE

TEST:	TEST SPECIFICATION(S):	RESULTS:
Partial Discharge	IEC 60664-1	≥ 1000 VDC
Dielectric Strength	UL 746 A	18 kV
Volume Resistivity		18 10 ¹⁴ ohm-cm
Comparative Tracking Index (CTI)		600V

WEATHERABILITY TESTING PERFORMANCE

TEST:	TEST SPECIFICATION(S):	RESULTS:
Damp Heat Testing	85°C, 85% RH IEC 61215	≥ 1000 hours
Heat Freeze Humidity	UL 1703, >10 cycles	>70% of initial mechanical proper ties retained
UV Stability	UL 746C	≥ 2000 Hours
MVTR	ASTM F1249	≤ 2.5 g/m ² per day

FLAME RESISTANCE TESTING PERFORMANCE

TEST:	TEST SPECIFICATION(S):	RESULTS:
Flame Spread Index	In accordance with ASTM E162	64
High Current Arc Ignition (HAI)	Exposed to 150 arcs with no ignition	PLC 0
Vertical Burn	(Protekt®/PET construction) Flammability VB Testing in accordance with IEC 60695-11-10	5VB

*Theoretical nominal
 This product is covered by one or more U.S. patents and pending U.S. and other patent applications.
 Please see www.madico.com/patents Typical Data – Not Specification



© 2016 Madico, Inc. V0796 4/16



Madico PhotoVoltaic Backsheets
 64 Industrial Parkway
 Woburn MA, 01801
 USA

Phone: 1-800-633-0140
 Fax: 1-781-935-6841
 Email: InfoSF@madico.com
www.madicopv.com