


## PRESERV A - K2N

'PRESERV A - 150 K2N' is a Non - Fluoro based, UV and weather stable, black Backsheet.

PRESERV A - 150 K2N can be used for all Crystalline and many Thin - Film PV modules.

### STRUCTURE



## PROPERTIES

Particulars	Test Method	Unit	Description	Values
Thickness	Micrometre	µm		320
Width	Scale	mm		Up to 1250
Tensile Strength @ max. load	ASTM D 882	MPa	MD TD	≥90 ≥90
Elongation @ break	ASTM D 882	%	MD TD	≥90 ≥90
Thermal Shrinkage @ 150°C, 30 min.	ASTM D 1204	%	MD TD	≤1.5 ≤0.5
Interlayer Adhesion Strength	ASTM D 903	N/cm	HPET/PET PET/PRIMER	≥5 ≥5
Adhesion Strength with Encapsulant	ASTM D 903	N/cm	Backsheet / EVA	≥70
Moisture Barrier - MVTR @ 38°C, 90% RH	ASTM F 1249	g/(m <sup>2</sup> - day)		≤1.5
System Voltage	IEC 61730 - 1	VDC		≥1000

Width: Up to 1000 mm - all sizes available. Sizes >1000 mm - make to order

**PACKING:** Unless specified, below is the standard packing of 'PRESERV'  
# Length/Roll: 100 metres | # No. of Rolls/Pallet: 12 or 16 |  
# Total Linear Metres/Pallet: 1200 or 1600  
# Each roll is sealed in a protective bag  
# Boxes are strapped on suitable pallets

**Note :** The above technical information represents the typical range of properties and is believed to be correct as on date. This data should however not be used to establish specification limits or used as basis for design. RenewSys gives no warranty and assumes no liability in connection with any use of this information and is subject to the RenewSys general terms and conditions.