



**ENERGY**  
PHOTOVOLTAIC  
**艾能聚光伏**  
www.energy-zj.com

为您专业创造  
太阳能晶体硅电池





www.energy-zj.com

# 125S

Mono 5" (R150)


125S0R2

Monocrystalline silicon solar cells




MECHANICAL DATA AND DESIGN		Efficiency(%)	Pmpp(W)	Ump(V)	Imp(A)	Uoc(V)	Isc(A)	FF(%)
Format	125mm×125mm±0.5mm	17.75-18.00	2.66	0.533	4.986	0.630	5.327	79.24
Thickness	190 μm±20 μm	17.50-17.75	2.62	0.528	4.959	0.629	5.297	78.60
Front (-)	1.9mm bus bars(silver), blue anti-reflecting coating(silicon nitride)	17.25-17.50	2.58	0.523	4.934	0.629	5.285	77.59
		17.00-17.25	2.54	0.519	4.906	0.628	5.270	76.74
Back (+)	3mm wide soldering pads(silver) back surface field(aluminium)	16.75-17.00	2.50	0.512	4.884	0.628	5.262	75.70
		16.50-16.75	2.47	0.509	4.861	0.627	5.254	75.00
TEMPERATURE COEFFICIENTS		16.25-16.50	2.43	0.507	4.798	0.626	5.245	74.07
TkVoltage	-0.348%/K	16.00-16.25	2.40	0.504	4.754	0.625	5.237	73.34
TkCurrent	+0.031%/K	15.75-16.00	2.36	0.502	4.696	0.624	5.228	72.34
TkPower	-0.46%/K	15.50-15.75	2.32	0.500	4.636	0.621	5.180	72.12

### IV CURVE



### SPECTRAL RESPONSE



### INTENSITY DEPENDENCE

Intensity [W/m²]	Isc*[mA]	Voc*[mV]
1000	1.0	1.000
900	0.9	0.994
500	0.5	0.968
300	0.3	0.942
200	0.2	0.922

\*Ratio of Voc(Isc) at reduced intensity to Voc(Isc) at 1000 W/m²

\*calibrated against fraunhofer ISE freiburg

浙江艾能聚光伏科技股份有限公司  
ZHEJIANG ENERGY PHOTOVOLTAIC TECHNOLOGY CO., LTD

地址: 中国浙江海盐澉浦六里集镇翠屏路北侧  
电话: +86-573-86567888

传真: +86-573-86567886  
邮编: 314301