



XS156B3-210R+ Monocrystalline X-Cells

XS156B3-210R+


Monocrystalline X-Cells

Dimension	156.75mm x 156.75mm ± 0.25mm
Diagonal	210mm ± 0.5mm (round chamfers)
Thickness(Si)	180µm ± 20µm, 200µm ± 20µm
Front	Anisotropically textured surface and dark silicon nitride anti-reflection coatings
Front	1.4mm silver busbars
Back	Full-surface aluminum back-surface field
Back	2.5mm (silver / aluminum) discontinuous soldering pads




► Features

- > High conversion efficiencies resulting in superior power output performance
- > Outstanding power output even in low light or high temperature conditions
- > Optimized design for ease of soldering and lamination
- > Long-term stability, reliability and performance
- > Low breakage rate
- > Color uniformity



► Production and Quality Control

- > Precision cell efficiency sorting procedures
- > Stringent criteria for color uniformity and appearance
- > Reverse current and shunt resistance screening
- > ISO9001, ISO14001 and OHSAS 18001 certificated
- > Calibrated against Fraunhofer ISE



* See the reverse side for more detail



XS156B3-210R+ Monocrystalline X-Cells

► Electrical Performance

		198	197	196	195
Efficiency	Eff(%)	19.80	19.70	19.60	19.50
Power	Ppm(W)	4.84	4.81	4.79	4.76
Max. Power Current	Ipm(A)	8.87	8.83	8.80	8.76
Short Circuit Current	Isc(A)	9.36	9.31	9.28	9.25
Max. Power Voltage	Vpm(V)	0.546	0.545	0.544	0.544
Open Circuit Voltage	Voc(V)	0.644	0.644	0.643	0.643
Efficiency Code		194	193	192	190
Efficiency	Eff(%)	19.40	19.30	19.20	19.00
Power	Ppm(W)	4.74	4.72	4.69	4.64
Max. Power Current	Ipm(A)	8.73	8.69	8.66	8.59
Short Circuit Current	Isc(A)	9.23	9.19	9.16	9.09
Max. Power Voltage	Vpm(V)	0.543	0.542	0.542	0.540
Open Circuit Voltage	Voc(V)	0.643	0.642	0.642	0.641


Standard test conditions: AM1.5, 1000W/m², 25°C. Average accuracy of all tested figures is ±1.5% rel.

► Temperature Coefficients


Current Temperature Coefficient	$\alpha(I_{SC})$	0.03%/°C
Voltage Temperature Coefficient	$\beta(V_{OC})$	-0.34%/°C
Power Temperature Coefficient	$\gamma(P_{MAX})$	-0.43%/°C

Standard test conditions : AM1.5, 1000W/m², 25°C.

► Spectral Response(SR)



► IV Curve



Specifications subject to change without prior notice.
MOTECH reserves the rights of final interpretation and revision of this datasheet.

Feb 2017 Vi2.3C_V05

MOTECH INDUSTRIES, INC. SOLAR DIVISION

Tainan Science Park | No.2, Dashun 9th Rd., Xinshi Dist., Tainan City,
74145, Taiwan

Tel: +886-6-5050789 Fax: +886-6-5051789

E-mail: sales_marketing@motech.com.tw

www.motechsolar.com