

AS-6M-xxxW

MONOCRYSTALLINE MODULE

ADVANCED PERFORMANCE & PROVEN ADVANTAGES

- High module conversion efficiency up to 18.81% by using high efficient solar cells and advanced manufacturing technology.
- Low degradation and excellent performance under high temperature and low light conditions.
- Robust aluminum frame ensures the modules to withstand wind loads up to 2400Pa and snow loads up to 5400Pa.
- High reliability against extreme environmental conditions.

CERTIFICATIONS

- IEC61215, IEC61730, CE, CQC, CGC, ETL(USA), JET(Japan), J-PEC(Japan), Kemco(South Korea), KS(South Korea), MCS(UK), FSEC(FL-USA), CSI Eligible(CA-USA), Israel Electric(Israel), InMetro(Brazil), TSE(Turkey)
- ISO9001:2008: Quality management system
- ISO14001:2004: Environmental management system
- OHSAS18001:2007: Occupational health and safety management system

SPECIAL WARRANTY

- 12 years limited product warranty.
- Limited linear power warranty: 12 years 91.2% of the nominal power output, 30 years 80.6% of the nominal power output.



Passionately

committed to

delivering innovative

energy solution



Worldwide Energy and Manufacturing (Nantong) Co., Ltd. www.weamerisolar.com, sales@weamerisolar.com

ELECTRICAL CHARACTERISTICS AT STC					
Maximum Power (P _{max})	350W	355W	360W	365W	
Open Circuit Voltage (V _{oc})	46.9V	47.1V	47.3V	47.5V	
Short Circuit Current (I _{SC})	9.57A	9.66A	9.75A	9.85A	
Voltage at Maximum Power (V_{mp})	38.3V	38.5V	38.7V	38.9V	
Current at Maximum Power (Imp)	9.14A	9.23A	9.31A	9.39A	
Module Efficiency (%)	18.04	18.30	18.55	18.81	
Operating Temperature	-40°C to +85°C				
Maximum System Voltage	1500V DC				
Fire Resistance Rating	Class C				
Maximum Series Fuse Rating	15A				

STC: Irradiance 1000W/m², Cell temperature 25°C, AM1.5; Binning Tolerance of Pmax: ±5W; Measurement Tolerance: ±3%

ELECTRICAL CHARACTERISTICS AT NOCT					
Maximum Power (P _{max})	258W	264W	268W	272W	
Open Circuit Voltage (V _{oc})	42.9V	43.9V	44.1V	44.3V	
Short Circuit Current (I _{SC})	7.84A	7.81A	7.87A	7.92A	
Voltage at Maximum Power (V _{mp})	34.6V	35.7V	35.9V	36.1V	
Current at Maximum Power (I_{mp})	7.46A	7.40A	7.47A	7.54A	


NOCT: Irradiance 800W/m², Ambient temperature 20°C, Wind Speed 1 m/s


MECHANICAL CHARACTERISTICS		
Cell type	Monocrystalline 5BB 156.75x156.75mm (6x6inches)	
Number of cells	72 (6x12)	
Dimensions	1956x992x35mm (77.01x39.06x1.38inches)	
Weight	23kg (50.7lbs)	
Front cover	3.2mm (0.13inches) tempered glass with AR coating	
Frame	Anodized aluminum alloy	
Junction box	IP67, 3 diodes	
Cable	4mm ² (0.006inches ²), 1000mm (39.37inches)	
Connector	PV-ZH202B(Manufacturer: Zhonghuan Sunter)	

TEMPERATURE CHARACTERISTICS		
Nominal Operating Cell Temperature (NOCT)	45°C±2°C	
Temperature Coefficients of P _{max}	-0.39%/°C	
Temperature Coefficients of V _{oc}	-0.29%/°C	
Temperature Coefficients of I _{SC}	0.052%/°C	

PACKAGING			
Standard packaging	30pcs/pallet		
Module quantity per 20' container	300pcs		
Module quantity per 40' container	660pcs(GP)/715pcs(HQ)		


IV CURVES






ENGINEERING DRAWINGS

Unit: mm





Rear View

Specifications in this datasheet are subject to change without prior notice.

Amerisolar and Amerisolar logo denoted with ® are registered trademarks of Worldwide Energy and Manufacturing (Nantong) Co., Ltd.