GEL121000BAG


NON-SPILLABLE RECHARGEABLE SEALED LEAD ACID BATTERY




FEATURES

- Design with flat plate, GEL electrolyte and AGM separator technology;
- GEL electrolyte inside of battery keeps uniformity condition, battery is with excellent cycle life;
- GEL electrolyte has huge thermal capacity, thermal runaway phenomena never occur;
- High strength ABS material for container & lid;
- Wide temperature scope of application (-15⁴⁵°C). Best temperature of application (20±5°C);
- No leaking, safe and reliable;
- Standing or lying down for using, convenient to transport and install;
- Low self-discharge rate.

DIMENSION



TERMINAL



Nominal Voltage	12V		C ₁₀	100Ah (10.5V, at 25°C)	
Nominal Capacity (C ₁₀)	100Ah (10.5V, at 25°C)	Consister	C ₅	80Ah (10.5V, at 25°C)	
	Length 407mm	Capacity	C ₃	75Ah (10.5V, at 25℃)	
Dimension	Width 173mm		C ₁	55Ah (10.2V, at 25°C)	
	Height 209.5mm	Internal Resistance		Approx. 6 mΩ (25°C)	
	Total Height 234.5mm	Max Short-duration Discharge Current 2000A(2000A(25℃)	
Weight	Approx. 35.65kg	Terminal		FP-05/RT-20	

■ SPECIFICATIONS

WUHAN CHANGGUANG BATTERY CO., LTD. www.cgb.com.cn

GEL121000BAG

NON-SPILLABLE RECHARGEABLE SEALED LEAD ACID BATTERY

■ CHARGE


Using Mode Charging Voltage		Temperature Compensation	Max Charging Current	
Standby Use	Standby Use 2.275±0.025V/cell (25°C) -3.3mV/°C/cell			
Cyclic Use	2.45±0.05V/cell (25°℃)	-5mV/°C/cell	30A	


STORAGE

- Batteries should be stored in dry and clean warehouse which has good air exchange system. Batteries should avoid direct sunlight. Batteries should not be near to heat (such as radiator, the distance should more than 1m). Batteries should avoid any toxic gas and organic solvent.
- When the ambient temperature is less than 25°C, the longest storage life is 6 months. If ambient temperature is higher, the longest storage life varies as specified in below chart.


Storage Temperature ($^{\circ}$ C)	≤25	26~33	34~40
Storage Time (Month)	6	3	1


 Batteries should be recharged within the storage life or before using. Charging methods: maximum charging current 30A, constant voltage 2.45±0.05V/cell (25°C); Charging time: 15~20h; Temperature compensation coefficient: -5mV/°C/cell.





Add: No.172, Checheng Road, Wuhan Economic & Technology Development Zone, Wuhan, China, 430056. Tel: (86)27-8489 1318 Fax: (86)27-8489 1924 E-mail: sales@cgbbattery.com





WUHAN CHANGGUANG BATTERY CO., LTD. www.cgb.com.cn