

# UN3.0-6 (6V3.0Ah/20hr)

The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and thus immobilized.

Should the battery be accidentally overcharged producing bydrogen and oxygen, Special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.

## **Battery Construction**


	Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Ī	Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

#### **General Feature**

- Absorbent Glass Mat(AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.

### **SPECIFICATION**

Nominal voltage	··· 6V
Number of cell	·· 3
Length(mm/inch) ······	·· 43/1.69
Width(mm/inch	47.5/1.87
Height(mm/inch) ······	·· 86/3.35
Total Height(mm/inch)	86/3.35
Approx. Weight(kg/lbs)	0.45/0.99



#### **Performance Characteristics**

	20 hour rate (0.15A \ 5.25V)	3.0Ah					
Capacity	10 hour rate (0.28A \ 5.25V)	2.8Ah					
77°F(25℃)	5 hour rate (0.52A \ 5.25V)	2.6Ah					
	1 hour rate (1.92A \ 4.8V)	1.92Ah					
Internal Resistance	Full charged Battery77°F(25°C):40mΩ						
Capacity	104° F(40°C)	102%					
affected by	77° F(25℃)	100%					
Temperature	32° F(10℃)	85%					
(20 hour rate)	5° F(-15℃)	65%					
Calf Diaghana	Capacity after 3 month storage	90%					
Self-Discharge 68°F(20°C)	Capacity after 6 month storage	80%					
08 F(20 C)	Capacity after 12month storage	60%					
Max. disc	Max. discharge current77°F(25°C): 45A(5S)						
Charge	Float: 6.8~6.9 V/77° F/(25°						
(Constant	Onstant Cycle:7. 25~7. 45 V/77°F/(25						
Voltage)	Max. Current: 0.75A						

#### Discharge Constant Current (Amperes at 77° F25 ${\bf C}$ )


End Point Volts/Cell	5min	10min	15min	30min	1h	3h	5h	10h	20h
1. 60V	11. 5	8. 30	5. 82	3. 35	1. 92	0. 86	0. 57	0. 30	0. 160
1. 65V	10. 9	7.90	5. 60	3. 23	1. 84	0. 83	0.56	0. 30	0. 155
1. 70V	10.3	7.50	5. 38	3. 11	1. 76	0.80	0. 54	0. 29	0. 155
1. 75V	9.70	7. 05	5. 13	2. 99	1. 68	0. 78	0.52	0. 28	0. 150
1. 80V	9.05	6. 60	4. 83	2. 85	1. 60	0. 73	0.49	0. 26	0. 140


#### Discharge Constant Power (watts at 77° F 25°C)


End Point Volts/Cell	5min	10min	15min	30min	45min	1h	2h	3h	5h
1. 60V	21.6	14. 4	11. 1	6.75	5. 02	3. 86	2. 13	1. 67	1. 15
1. 65V	20. 3	13. 6	10.5	6.40	4.79	3.70	2.07	1.63	1. 13
1. 70V	19. 0	12. 7	9. 88	6.06	4. 55	3. 52	1. 99	1.59	1. 10
1. 75V	17. 7	11. 9	9. 30	5. 71	4. 30	3. 35	1. 92	1.54	1. 08
1. 80V	16. 3	11. 1	8. 69	5. 36	4. 05	3. 16	1. 83	1. 49	1. 05


(Note)The above characteristics data are average values obtained Within three charge/discharge cycles not the minimum values.























### DONGGUAN OREMA POWER CO., LTD

Add: #1 Qilinling Road Shahu, Tangxia Town, Dongguan Guangdong China

TEL: +86-769- 3896 1163 +86-769- 3896 1168

FAX: +86-769- 3896 1169







www.oremabattery.com