



3FM7 (6V7Ah)

LONGWAY® Standard battery is design for a general purpose by KaiYing Power. 3FM7A is a general purpose battery up to 5 years in star service or more than 260 cycles at 100% discharge in cycle service. As with all LONGWAY® batteries, all are rechargeable highly efficient, leak proof and maintenance free.
















Cells per Unit	3				
Normal Voltage	6V				
Capacity	7Ah@20Hr-rate to 1.75V per cell@25°C				
Weight	Approx. (1.00±3%)kg(2.21bs)				
Maximum Discharge Current	70A(5sec)				
Internal Resistance	Approx. 26mΩ full charged @25℃				
Operating Temperature Range	Discharge: -20°C~60°C				
	Charge: 0°C~50°C				
	Storage: -20°C~60°C				
Nominal Operating Temperature Range	25℃±3℃				
Float Charging Voltage	6.75~6.9VDC/unit Average @25°C				
Maximum Charging Current	2.1A				
Equalization and Cycle Service	7.20V~7.50VDC/unit Average @ 25°C				
Self Discharge	LONGWAY Valve Regulated Lead Acid (VRLA) batteries can be stored				
	for more than 6 months at 25°C. Self-discharge ratio less than 3%				
	per month at 25℃. Please charge batteries before using.				
Terminal	F1(0.187)/F2(0.250)				
Container Material	ABS(UL94-HB)				
	*Flammability resistance of (UL94-V0) can be available upon request				

Dimensions: L151*W36*H94(TH100)mm







Constant Current Discharge Characteristics (A, 25 \mathcal{C})


F.V/TIME	5min	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
4.80	29.54	20.02	15.47	7.560	4.480	2.475	1.838	1.133	0.765	0.661	0.355
4.95	28.65	19.22	15.16	7.182	4.346	2.462	1.825	1.122	0.763	0.658	0.354
5.10	28.06	19.02	14.70	7.106	4.301	2.450	1.820	1.120	0.759	0.655	0.351
5.25	27.18	18.42	14.08	6.804	4.122	2.426	1.784	1.086	0.756	0.652	0.351
5.40	26.38	17.88	13.95	6.804	4.086	2.401	1.765	1.075	0.756	0.651	0.350

Constant Power Discharge Characteristics (Watt, 25 \mathcal{C})


F.V/TIN	/IE 5min	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
4.80	164.8	112.9	88.18	43.32	25.94	14.48	10.92	6.767	4.590	3.965	2.129
4.95	159.9	108.4	86.42	41.15	25.16	14.40	10.84	6.700	4.577	3.945	2.121
5.10	156.6	107.3	83.77	40.72	24.90	14.33	10.81	6.686	4.554	3.929	2.108
5.25	151.6	103.9	80.24	38.99	23.86	14.19	10.59	6.486	4.536	3.914	2.104
5.40	147.2	100.8	79.54	38.99	23.66	14.05	10.49	6.419	4.536	3.906	2.100




Float Service Life




Capacity Retention Characteristic




Battery Voltage and Charge Time for Standby use




Cycle Service Life



Battery Voltage and Charge Time for Cycle Use



Terminal Voltage (V) and Discharge Time



Charging Procedures

A = = E = = # = =	CI	Max. Charge		
Application	Temperature	Set Point	Allowable Range	Current
Cycle Use	25°C(77°F)	2.45	2.40~2.50	0.00
Standby	25°C(77°F)	2.275	2.25~2.30	- 0.3C

Discharge Current VS. Discharge Voltage

Final Discharge Voltage V/cell	1.75	1.70	1.65	1.60
Discharge	0.202(A)	0.2C<(A)	0.5C<(A)	(A)>4.00
Current (A)	0.2C>(A)	<0.5C	<1.0C	(A)>1.0C

KaiYing Power Supply & Electrical Equip Co., Ltd.

Address: KaiYing Industrial Park, ChengXiang Town, Anxi, Quanzhou, Fujian China

Tel:86-595-68782266 Fax: 86-0595-68782222

Website: www.longwaybattery.com Email: Sales@Jongwaybattery.com

KY-IOP-LW6-7 AO. October 2014