

<u>6FM9Y (12V9Ah)</u>

9Ah@20Hr-rate to 1.75V per cell@25°C

Approx.(2.50±3%)kg (5.51lbs)

Discharge: -20℃~60℃ Charge: 0℃~50℃ Storage: -20℃~60℃

F1(0.187)/F2(0.250)

ABS(UL94-HB)

Approx. 26mΩ full charged @25°C

13.7~13.9VDC/unit Average @25°C

14.4V~15.0VDC/unit Average @ 25°C

6

12V

90A(5sec)

25℃±3℃

2.7A



Specifications:

Maximum Discharge Current

Operating Temperature Range

Nominal Operating Temperature Range

Cells per Unit

Capacity Weight

Normal Voltage

Internal Resistance

Float Charging Voltage

Self Discharge

Container Material

Terminal

Maximum Charging Current

Equalization and Cycle Service

LONGWAY® Standard battery is design for a general purpose by KaiYing Power. 6FM9 is a general purpose battery up to 5 years in star service or more than 260 cycles at 100% discharge in cycle service. As with all **LONGWAY®** batteries, all are rechargeable highly efficient, leak proof and maintenance free.

LONGWAY Valve Regulated Lead Acid (VRLA) batteries can be stored

for more than 6 months at 25° C. Self-discharge ratio less than 3%

*Flammability resistance of (UL94-V0) can be available upon request

per month at 25°C. Please charge batteries before using.













Dimensions: L225*W47*H100 (TH106)mm





Constant Current Discharge Characteristics (A, 25 ${ m C}$)

		-			-						
F.V/TIME	5min	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
9.60	33.8	21.2	16.2	9.45	5.85	3.20	2.28	1.55	1.00	0.82	0.45
9.90	32.7	20.5	15.8	9.21	5.70	3.18	2.27	1.55	1.00	0.82	0.45
10.2	32.1	20.1	15.6	9.07	5.62	3.15	2.25	1.53	0.99	0.81	0.45
10.5	31.1	19.5	15.1	8.79	5.44	3.12	2.23	1.51	0.99	0.81	0.44
10.8	30.1	18.9	14.8	8.62	5.34	3.09	2.21	1.50	0.98	0.81	0.44

Constant Power Discharge Characteristics (Watt, 25 $^{\circ}$ C)

F.V/TIME	5min	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
9.60	367	239	185	108	67.7	37.4	27.1	18.5	12.1	9.87	5.48
9.90	365	231	180	106	66.0	37.2	27.0	18.5	12.0	9.88	5.49
10.2	358	227	177	104	65.0	36.9	26.7	18.3	11.8	9.78	5.43
10.5	347	219	172	101	63.0	36.5	26.5	18.1	11.9	9.75	5.42
10.8	336	213	168	99	61.8	36.1	26.2	17.9	11.8	9.72	5.40



Discharge

Depth 30%

1200

mperature

25°C 77°F

■ 20°C 68°F

0.09C 0.05C

Ambient T


25°C (77°

1000

800

Terminal Voltage (V) and Discharge Time

Capacity Retention Characteristic



120

100

80

60

40

20 0

13

12

11

10

9

8

0

2 3

Terminal Voltage (V)

Discharge

200

Depth 100%

Discharge


Depth 50%

600


Number of Cycles (Times)

400

Capacity (%)



Battery Voltage and Charge Time for Cycle Use



ic

Discharge Current VS. Discharge Voltage

5 Hr

10

20 30

-

0.250

1

0.60

60 2 3

5 Min 20 30 Discharge Time (Min)

10

Charging Procedures

Application	C	Max. Charge		
	Temperature	Set Point	Allowable Range	Current
Cycle Use	25°C(77°F)	2.45	2.40~2.50	
Standby	25℃(77°F)	2.275	2.25~2.30	0.3C

Final Discharge Voltage V/cell	1.75	1.70	1.65	1.60
Discharge	0.005(0)	0.2C<(A)	0.5C<(A)	(4)>4.00
Current (A)	0.2C>(A)	<0.5C	<1.0C	(A)>1.0C

KaiYing Power Supply & Electrical Equip Co., Ltd.

Address: KaiYing Industrial Park, ChengXiang Town, Anxi, Quanzhou, Fujian China

Tel:86-595-68782266 Fax: 86-0595-68782222

Website: www.longwaybattery.com Email: Sales@longwaybattery.com