



Specifications:

Maximum Discharge Current

Operating Temperature Range

Nominal Operating Temperature Range

Cells per Unit

Capacity Weight

Normal Voltage

Internal Resistance

Float Charging Voltage

Self Discharge

Container Material

Terminal

Maximum Charging Current

Equalization and Cycle Service

6FM26G (12V26Ah)

26Ah@20Hr-rate to 1.75V per cell@25°C

Approx. (8.4±3%) kg (18.52lbs)

Approx. 10mΩ full charged @25°C

13.7~13.9VDC/unit Average @25°C

14.4V~15.0VDC/unit Average @ 25°C

Discharge: -20℃~60℃ Charge: 0℃~50℃ Storage: -20℃~60℃

6

12V

260A(5sec)

25℃±3℃

6.5A

F5/F8

ABS(UL94-HB)

LONGWAY® Standard battery is design for a general purpose by KaiYing Power. 6FM26G is a general purpose battery up to 8 years in float service or more than 260 cycles at 100% discharge in cycle service. As with all **LONGWAY®** batteries, all are rechargeable highly efficient, leak proof and maintenance free.














Dimensions: L175*W166*H126(TH126)









LONGWAY Valve Regulated Lead Acid (VRLA) batteries can be stored

for more than 6 months at 25° C. Self-discharge ratio less than 3%

*Flammability resistance of (UL94-V0) can be available upon request

per month at 25°C. Please charge batteries before using.





Constant Current Discharge Characteristics (A, 25 ${\cal C}$)


F.V/TIME	5min	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
9.60	77.5	64.0	50.2	30.6	16.9	10.2	7.65	4.91	3.17	2.64	1.39
9.90	75.2	62.0	49.2	29.9	16.6	10.1	7.62	4.88	3.15	2.63	1.38
10.2	73.6	60.8	48.2	29.3	16.2	10.0	7.54	4.84	3.14	2.62	1.37
10.5	69.3	58.8	46.7	28.4	15.7	9.9	7.46	4.79	3.13	2.61	1.37
10.8	63.5	57.1	45.8	27.9	15.4	9.8	7.39	4.74	3.12	2.60	1.37


Constant Power Discharge Characteristics (Watt, 25 ${ m C}$)

F.V/TIME	5min	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
9.60	837	698	558	343	193	118	90.0	58.0	38.0	31.5	16.6
9.90	812	677	541	336	189	117	89.6	57.7	37.8	31.4	16.5
10.2	795	664	529	329	185	116	88.7	57.2	37.7	31.2	16.5
10.5	749	643	513	319	179	115	87.8	56.6	37.6	31.1	16.4
10.8	686	624	503	313	176	114	86.9	56.0	37.4	31.0	16.4




Capacity Retention Characteristic





Battery Voltage and Charge Time for Cycle Use



Charging Procedures

Application	CI	Max. Charge			
Application	Temperature	Set Point	Allowable Range	Current	
Cycle Use	25°C(77°F)	2.45	2.40~2.50	0.050	
Standby	25℃(77°F)	2.275	2.25~2.30	- 0.25C	


•	Final Discharge Voltage V/cell	1.75	1.70	1.65	1.60
_	Discharge	0.2C>(A)	0.2C<(A)	0.5C<(A)	(A)>1.0C
	Current (A)	0.2C/(A)	<0.5C	<1.0C	(A)>1.0C

KaiYing Power Supply & Electrical Equip Co., Ltd.


Address: KaiYing Industrial Park, ChengXiang Town, Anxi, Quanzhou, Fujian China

Tel:86-595-68782266 Fax: 86-0595-68782222


Website: www.longwaybattery.com Email: Sales@longwaybattery.com



Cycle Service Life



Terminal Voltage (V) and Discharge Time



Discharge Current VS. Discharge Voltage

KY-IOI	P-LW12-26G	AO. May	2015