



# 6FM30G (12V30Ah)

**LONGWAY®** Standard battery is design for a general purpose by KaiYing Power. 6FM30G is a general purpose battery up to 8 years in float service or more than 260 cycles at 100% discharge in cycle service. As with all **LONGWAY®** batteries, all are rechargeable highly efficient, leak proof and maintenance free.

6
12V
30Ah@10Hr-rate to 1.80V per cell@25℃
Approx.(9.5±3%) kg (20.94lbs)
300A(5sec)
Approx. 9.8mΩ full charged @25°C
Discharge: -20℃~60℃
Charge: 0℃~50℃
Storage: -20℃~60℃
<b>25</b> ℃± <b>3</b> ℃
13.7~13.9VDC/unit Average @25℃
7.5A
14.4V~15.0VDC/unit Average @ 25°C
LONGWAY Valve Regulated Lead Acid (VRLA) batteries can be stored
for more than 6 months at $25^{\circ}C(77^{\circ}F)$ . Self-discharge ratio less than 3%
per month at $25^{\circ}\mathbb{C}(77^{\circ}F)$ . Please charge batteries before using.
Terminal F15
ABS(UL94-HB)
*Flammability resistance of (UL94-V0) can be available upon request












# CE

## Dimensions: L195\*W130\*H161(TH166)mm








## Constant Current Discharge Characteristics (A, 25 ${ m C}$ )

					,						
F.V/TIME	5min	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
9.60	89.4	73.8	58.0	35.3	19.5	11.7	8.8	5.7	3.65	3.05	1.60
9.90	86.7	71.6	56.8	34.5	19.1	11.7	8.8	5.6	3.64	3.03	1.59
10.2	84.9	70.1	55.6	33.8	18.7	11.6	8.7	5.6	3.62	3.02	1.58
10.5	80.0	67.9	53.9	32.8	18.1	11.4	8.6	5.5	3.61	3.01	1.58
10.8	73.3	65.9	52.9	32.1	17.8	11.3	8.5	5.5	3.60	3.00	1.58
Constant Power Discharge Characteristics (Watt, 25 ${ m C}$ )											


-												
	F.V/TIME	5min	10min	15min	30min	60min	2h	3h	5h	8h	10h	20h
	9.60	966	806	643	396	222	136	104	67	43.8	36.4	19.2
	9.90	937	782	624	388	218	135	103	67	43.6	36.2	19.1
	10.2	917	766	611	380	213	134	102	66	43.5	36.0	19.0
	10.5	864	741	592	368	207	132	101	65	43.3	35.9	19.0
	10.8	792	720	580	361	203	131	100	65	43.2	35.8	18.9




#### **Capacity Retention Characteristic**







Battery Voltage and Charge Time for Cycle Use



#### **Charging Procedures**

Application	CI	Max. Charge		
	Temperature	Set Point	Allowable Range	Current
Cycle Use	25°C(77°F)	2.45	2.40~2.50	0.050
Standby	25℃(77°F)	2.275	2.25~2.30	0.25C


Final Discharge Voltage V/cell	1.75	1.70	1.65	1.60
Discharge	0.2C>(A)	0.2C<(A)	0.5C<(A)	(4)>1.00
Current (A)		<0.5C	<1.0C	(A)>1.0C

KaiYing Power Supply & Electrical Equip Co., Ltd.


Address: KaiYing Industrial Park, ChengXiang Town, Anxi, Quanzhou, Fujian China

Tel:86-595-68782266 Fax: 86-0595-68782222


Website: www.longwaybattery.com Email: Sales@longwaybattery.com



**Cycle Service Life** 



Terminal Voltage (V) and Discharge Time



Discharge Current VS. Discharge Voltage

KY-IOP-LW12-30G AO, May 2015	