
HJTG12645W



120-cell Bifacial HJT Half Cell Double-glass Solar Module





HJT 2.0 Technology

Combining gettering process and single-side μ c-Si technology to ensure higher cell efficiency and higher module power.



-0.26%/℃ Pmax temperature coefficient

More stable power generation performance and even better in hot climate.



SMBB design with Half-Cut Technology

Shorter current transmission distance, less resistive loss and higher cell efficiency.



Up to 90% Bifaciality

Natrual symmetrical bifacial structure bringing more energy yield from the backside.



Sealing with PIB based sealant

Stronger water resistance, greater air impermeability to extent module lifespan.



Higher reliability

Industrial leading product and performance warranty, ensuring modules' consistent outstanding performance.



Suitable for Utility project

Lower BOS cost, lower LCOE

WARRANTY

Product Warranty 15 years

Linear Power Warranty







HJTG12645W




Flectrical Characteristics (STC*)

120-cell Bifacial HJT Half Cell Solar Module

Engineering Drawings

Unit: mm



HJTG12645W	TS625	TS630	TS635	TS640	TS645		
Maximum Power (Pma:	k) 625W	630W	635W	640W	645W		
Module Efficiency (%	22.08%	22.26%	22.44%	22.61%	22.79%		
Optimum Operating Voltage (Vmp	o) 37.86V	38.03V	38.19V	38.35V	38.51V		
Optimum Operating Current (Imp) 16.51A	16.57A	16.63A	16.69A	16.75A		
Open Circuit Voltage (Vo	45.13V	45.30V	45.48V	45.65V	45.82V		
Short Circuit Current (Iso) 17.31A	17.37A	17.43A	17.49A	17.55A		
Operating Module Temperature			-40 ~ +85 °C				
Maximum System Voltage			C1500V (IEC)			
Maximum Series Fuse		30A					
Power Tolerance	_	0~+5W					
Bifaciality	_	85%±5%					

BSTC**						
Maximum Power	(Pmax)	690W	695W	700W	705W	710W
Optimum Operating Voltage	(Vmp)	37.86V	38.03V	38.19V	38.35V	38.51V
Optimum Operating Current	(Imp)	18.23A	18.28A	18.33A	18.39A	18.44A
Open Circuit Voltage	(Voc)	45.13V	45.30V	45.48V	45.65V	45.82V
Short Circuit Current	(lec)	10.111	10.164	10.211	40.274	40.224

^{**}BSTC: Front side irradiation 1000W/m², back side reflection irradiation 135W/m², AM=1.5, ambient temperature 25 °C.

Temperature Characteristics

Nominal Operating Cell Temp. (NOCT)	44 °C ± 2 °C		
Temperature Coefficient of Pmax	-0.26%/°C		
Temperature Coefficient of Voc	-0.24%/°C		
Temperature Coefficient of Isc	0.04%/°C		

Safety & Warranty					
Safety Class	Class II				
Product Warranty	15 yrs Workmanship				
Performance Warranty	30 yrs Linear Warranty*				

 $^{^\}star$ Less than 1% attenuation in the 1st year, the annual attenuation from the 2nd year is no more than 0.375%, and the power is no less than 88% until the 30th year.



		PERC Stand	lard	HJT M	odule	
100% 99%						
95%					90%	
90%					70 /0	88%
85%						
80%						
75%						
0 Befor to TENC	5 (INC atou	10 ndard warranty for d	15	20	25	30
* Relef to TENG	ring star	idard warranty for d	etaiis			

Shipping Configurations			
		HC	
Container Size		40'	
Pallets Per Container		18	
Modules Per Pallet	(pcs)	31	
Modules Per Container	(pcs)	558	

Tengying New Energy Technology Co.,Ltd

🖷 No.155 Xuezhi Road, Shapingba District, Chongqing, China