

FLOODED DEEP CYCLE BATTERY







Warranty	5 Years
BCI	SPEC
Plates/Cell	11
Flag L	
S/S Hex Cap Screw, Nut, Lock & Flat Washer	
5/16"-18	
19" 4/0 interconnect cables *RE incl.	
	BCI Plates/Cell Flag L S/S Hex Cap Screw, Nut, Lock 5/16"-18

Charge		
Charge Voltage Range	14.7-15 V/cell @ 25°C (77°F)	
Recommended Charge Current	45 A	
Maximum Charge Current	70 A	
Self-Discharge Rate	5%-10% per month at 25°C (77°F)	
Canacity		

Capacity				
Cold Crank Amps (CCA) 0°F / -18°C		871		
Marine Crank Amps (MCA) 32°F / 0°C		1088		
Reserve Capacity (RC @ 25A)		891 N	Minutes	
Reserve Capacity (RC @ 75A)		297 N	Minutes	
Capacity Affect by Temperature	40°C (104°F)	25°C (77°F)	0°C (32°F)	-15°C (5°F)
	105%	100%	75%	50%

Hour Rate	Capacity / AMP Hour	Current / AMPs
@ 100 Hour Rate	479 AH	4.79 A
@ 72 Hour Rate	453 AH	6.29 A
@ 50 Hour Rate	429 AH	8.58 A
@ 20 Hour Rate	371 AH	18.56 A
@ 15 Hour Rate	345 AH	23.02 A
@ 10 Hour Rate	330 AH	33.04 A
@ 8 Hour Rate	319 AH	39.91 A
@ 5 Hour Rate	297 AH	59.40 A
@ 1 Hour Rate	167 AH	167.08 A


Ampere hour capacity ratings based on specific gravity of 1.280 at 27°C (80°F). Reduce capacities 5% for specific gravity of 1.265 and 10% for 1.250.

Specifications			
Orality Orality	Weight	123 kg	271 lbs
	Length	55.9 cm	22"
	Width	28.6 cm	11.25"
	Height Inc. Term.	46.4 cm	18.25"

Product measurements & weights are calculated based on sample data. Individual specifications are subject to vary due to the manufacturing process & battery components.

Electrolyte Reserve	95 mm	3.75"	
Container (Inner)	Polypropylene		
Cover (Inner)	Polypropylene - heat sealed to inner container		
Container (Outer)	High Density Polypropylene		
Cover (Outer)	High Density Polypropylene snap fit to outer container		
Handles	Molded		
Notes	IEC 61427-1:2013		

Cycle Life vs. Depth of Discharge



DISCHARGE 0% 25% 50% 75% 100% 20 HR AH RATE 2.10 V 2.05 V 2.02 V 1.96 V 1.75 V 6 HR AH RATE 2.10 V 2.04 V 2.00 V 1.95 V 1.75 V 1 HR AH RATE 2.10 V 2.03 V 1.99 V 1.94 V 1.75 V

Rev.#3 | May 2019