Q.PEAK DUO M-G11S+ SERIES



400-420 Wp | 108 Cells 21.5% Maximum Module Efficiency

MODEL Q.PEAK DUO M-G11S+





Breaking the 21% efficiency barrier

Q.ANTUM DUO Technology with optimized module layout boosts module power.



A reliable investment

Inclusive 25-year product warranty and 25-year linear performance warranty¹.



Enduring high performance

Long-term yield security with Anti LeTID Technology, Anti PID Technology², and Hot-Spot Protect.



Extreme weather rating

High-tech aluminium alloy frame, certified for high snow (8100 Pa) and wind loads (4000 Pa).



Innovative all-weather technology

Optimal yields, whatever the weather with excellent low-light and temperature behaviour.



The most thorough testing programme in the industry

Qcells is the first solar module manufacturer to pass the most comprehensive quality programme in the industry: The new "Quality Controlled PV" of the independent certification institute TÜV Rheinland.














¹ See data sheet on rear for further information.

² APT test conditions according to IEC/TS 62804-1:2015, method A (-1500 V, 96 h)

■ Mechanical Specification

Format	1722 mm × 1134 mm × 30 mm (including frame)					
Weight	21.1 kg					
Front Cover	3.2 mm thermally pre-stressed glass with anti-reflection technology					
Back Cover	Composite film					
Frame	Black anodised aluminium					
Cell	6 × 18 monocrystalline Q.ANTUM solar half cells					
Junction box	53-101 mm × 32-60 mm × 15-18 mm Protection class IP67, with bypass diodes					
Cable	4 mm² Solar cable; (+) ≥1265 mm, (-) ≥1265 mm					
Connector	Stäubli MC4, Hanwha Q CELLS HQC4; IP68					



■ Electrical Characteristics

POWER CLASS			400	405	410	415	420
MINIMUM PERFORMANCE A	T STANDARD TEST CONDITIONS, ST	C1 (POWER TO	DLERANCE +5 W/-0) W)			
Power at MPP ¹	P_{MPP}	[W]	400	405	410	415	420
Short Circuit Current ¹	I _{sc}	[A]	13.88	13.91	13.95	13.99	14.03
Open Circuit Voltage ¹	V _{oc}	[V]	37.06	37.09	37.11	37.14	37.17
Current at MPP	I _{MPP}	[A]	13.16	13.23	13.30	13.37	13.44
Voltage at MPP	V_{MPP}	[V]	30.40	30.62	30.83	31.05	31.26
Efficiency ¹	η	[%]	≥20.5	≥20.7	≥21.0	≥21.3	≥21.5
MINIMUM PERFORMANCE A	T NORMAL OPERATING CONDITION	S, NMOT ²					
Power at MPP	P_{MPP}	[W]	300.1	303.8	307.6	311.3	315.1
Short Circuit Current	I _{sc}	[A]	11.18	11.21	11.24	11.27	11.30
Open Circuit Voltage	V _{oc}	[V]	34.95	34.97	35.00	35.03	35.05
Current at MPP	luna	ΓΔ1	10.34	10.41	10.47	10.53	10.59


29.01

 $^{1}\text{Measurement tolerances P}_{\text{MPP}} \pm 3\,\%; I_{\text{SC}}; V_{\text{OC}} \pm 5\,\% \text{ at STC: } 1000\,\text{W/m}^{2}, 25 \pm 2\,^{\circ}\text{C}, \text{AM 1.5 according to IEC } 60904\text{-}3 \bullet ^{2}800\,\text{W/m}^{2}, \text{NMOT, spectrum AM 1.5 } 1.5\,\% \text{ at STC: } 1000\,\text{W/m}^{2}, 25 \pm 2\,^{\circ}\text{C}, \text{AM 1.5 according to IEC } 60904\text{-}3 \bullet ^{2}800\,\text{W/m}^{2}, \text{NMOT, spectrum AM 1.5 } 1.5\,\% \text{ at STC: } 1000\,\text{W/m}^{2}, 25 \pm 2\,^{\circ}\text{C}, \text{AM 1.5 according to IEC } 60904\text{-}3 \bullet ^{2}800\,\text{W/m}^{2}, \text{NMOT, spectrum AM 1.5 } 1.5\,\% \text{ at STC: } 1000\,\text{W/m}^{2}, 25 \pm 2\,^{\circ}\text{C}, \text{AM 1.5 according to IEC } 60904\text{-}3 \bullet ^{2}800\,\text{W/m}^{2}, \text{NMOT, spectrum AM 1.5 } 1.5\,\% \text{ at STC: } 1000\,\text{W/m}^{2}, 25 \pm 2\,^{\circ}\text{C}, \text{AM 1.5 according to IEC } 1000\,\text{W/m}^{2}, \text{NMOT, spectrum AM 1.5 } 1.5\,\% \text{ at STC: } 1000\,\text{W/m}^{2}, 1000\,\text{W/m}^{2$

[V]

Qcells PERFORMANCE WARRANTY

Voltage at MPP



At least 98% of nominal power during first year. Thereafter max. 0.5% degradation per year. At least 93.5% of nominal power up to 10 years. At least 86% of nominal power up to 25 years.

All data within measurement tolerances. Full warranties in accordance with the warranty terms of the Qcells sales organisation of your respective country.

*Standard terms of guarantee for the 5 PV companies with the highest production capacity in 2021 (February 2021)


PERFORMANCE AT LOW IRRADIANCE

29 20

29.38

29.56

29.74



Typical module performance under low irradiance conditions in comparison to STC conditions (25 °C, 1000 W/m²).

TEMPE	RATURE COEFFICIENTS							
Tempera	ature Coefficient of I _{sc}	α	[%/K]	+0.04	Temperature Coefficient of Voc	β	[%/K]	-0.27
Tempera	ature Coefficient of P _{MPP}	γ	[%/K]	-0.34	Nominal Module Operating Temperature	NMOT	[°C]	43±3

■ Properties for System Design

Maximum System Voltage	V_{sys}	[V]	1000	PV module classification	Class II
Maximum Reverse Current	I _R	[A]	25	Fire Rating based on ANSI/UL 61730	C/TYPE 2
Max. Design Load, Push/Pull		[Pa]	5400/2665	Permitted Module Temperature	-40°C - +85°C
Max. Test Load, Push/Pull		[Pa]	8100/4000	on Continuous Duty	

■ Qualifications and Certificates

Quality Controlled PV -TÜV Rheinland; IEC 61215:2016; IEC 61730:2016. This data sheet complies with DIN EN 50380.





ocells

