



ORISun N-Type OSD9DH7216H TOPCon High-Efficiency Dual Glass Solar Module With MBB Technology



Intelligent Manufacturing, High-Performance N-type Solar cell

Industry-leading intelligent and efficient production lines, with the highest quality standards in the industry. Ensuring the most cost-effective production.



Higher Yield

High power, low temperature coefficient, high bifaciality ensuring the product can generate more energy benefits even in cloudy or hot weather with the same area. The bifaciality power gain increases with the backside illumination which can reach up to 25% or more.

	~	
F		3
	\mathbf{X}	\boldsymbol{J}
	$\mathbf{\mathbb{Z}}$	

Extremely Durable

Thanks to the optimal material matching and interconnection encapsulation technology, the product has outstanding module weather resistance performances. The overall module has passed the certification of 2400Pa wind load and 5400Pa snow load, while minimizing the degradation caused by PID.



Guaranteed Reliability

Industry leading 30 year product and performance linear warranty. Adopting the most advanced N-type mass production technology to ensure low LID and LETID degradation.



Extremely Elegant

Simple and elegant industrial design, suitable for various application scenarios.



605-625 Watt Higher Energy Output

Mechanical Structure Specifications


Dimensions	2382 x 1134 x 30 mm / 93.5 x 44.7 x 1.2 in
Weight	33.6 kg / 74.1 lbs
Front Material	Tempered high transparency photovoltaic glass, 2.0 mm / 0.08 in, anti reflective film
Back Material	Semi tempered photovoltaic glass, 2.0 mm / 0.08 in,
Frame	Anodized aluminum alloy
Cell Type	144Half piece, N-type monocrystalline silicon bifacial TOPCon solar cells
Junction Box	Protection grade IP68
Cable	Wireway: 4 mm²/TÜV, Length (+):300 mm/11.81 in & (-):200 mm

Packaging and Transportation



Transport by container or truck. For truck freight, each pallet has a loading capacity of 17.5 meters and a height of 3.5-4.5 meters.

Module Electrical Performance Specifications¹




Module model	Efficiency	Power*	Short-circuit current	Open circuit current	Optimal operating current	Optimum operating voltage
	η	Pmax	lsc	Voc	Impp	Vmpp
	[%]	[W]	[A]	[V]	[A]	[\]
	STC ²	NOCT ³ STC	NOCT STC	NOCT STC	NOCT STC	NOCT STC
605	22.40	455 605	11.61 14.66	49.58 52.19	11.25 14.04	40.45 43.10
610	22.58	459 610	11.63 14.71	49.79 52.41	11.29 14.08	40.67 43.31
615	2 2 .77	463 615	11.67 14.76	50.04 52.67	11.32 14.13	40.89 43.52
620	22.95	467 620	11.71 14.81	50.24 52.88	11.35 1 4.16	41.14 43.77
625	23.14	471 625	11.76 14.85	50.67 53.02	11.38 14.20	41.39 44.01

* (Power tolerance 0 W / +5 W for STC)

Bifacial Power Generation Performance (Rearside gain)

			· · · · ·			
5%	Pmax	635Wp	641Wp	646Wp	651Wp	656Wp
3%	Efficiency	23.52%	23.71%	23.9 1%	24.10%	24.29%
1.607	Pmax	696Wp	702Wp	707Wp	713Wp	719Wp
15%	Efficiency	25.76%	25.97%	26.18%	26.40%	26.6 1%
0.577	Pmax	756Wp	763Wp	769Wp	775Wp	781Wp
25%	Efficiency	28.00%	28.23%	28.46%	28.69%	28.92%

I-V Curve Under Different Illuminances



System Related Technical Parameters

Maximum system voltage	[V]	1500
Maximum rated fuse current	[A]	30
Security level		
Fire rating(UI61730)		А
Operating temperature range	[°C]	-40 to +85
Reference bifacial factor	[%]	80±5

Related Certifications

IEC IEC 61215:2016, IEC 61730:2016, UL 61730-1, UL 61730-2, PID (IEC 62804), Salt Mist (IEC 61701)


Note: All data and specifications are preliminary and may change without notice. For installation and operation instructions, please refer to the installation guide.

Temperature Coefficient

Isc TEMP coefficient	a	[%/K]	+0.045
Voc TEMP coefficient	β	[%/K]	-0.25
Pmpp TEMP coefficient	γ	[%/K]	-0.29
Nominal operating TEMP	NOCT	[°C]	45±2

The temperature coefficient described is a linear value.

Industry Leading Linear Quality Assurance



Passed Multiple IEC Standards With 3x Reliability And Weather Resistance Testing Procedures

1x IEC 3x IEC

Average Standard

The Lowest Testing Level Of Orisolar

 Power test according to IEC 60904-3, test tolerance: 0~+3%
² STC condition: Light intensity 1000 W/m², Component temperature 25 ° C, AM1.5G spectral conditions

 $^{\rm s}$ NMOT: nominal component operating temperature, light intensity 800 W/m $^{\rm 2},$ AM1.5G spectral conditions, ambient temperature 20 $^{\circ}$ C

