





AOLI SOLAR

## Monocrystalline Solar Cells 158.75mm 9BB




Eff (%)	Pmpp (W)	Umpp (V)	Impp (A)	Uoc (V)	Isc (A)	FF (%)
22.2	5.59	0.578	9.777	0.682	10.324	79.86
22.1	5.57	0.577	9.757	0.681	10.307	79.83
22.0	5.54	0.576	9.740	0.680	10.294	79.75
21.9	5.52	0.574	9.725	0.679	10.281	79.69
21.8	5.49	0.573	9.713	0.677	10.267	79.64
21.7	5.47	0.570	9.704	0.675	10.254	79.60
21.6	5.44	0.568	9.695	0.673	10.240	79.52
21.5	5.42	0.566	9.690	0.672	10.236	79.34
21.4	5.39	0.563	9.683	0.668	10.223	79.20
21.3	5.37	0.560	9.672	0.665	10.214	79.15
21.1	5.32	0.557	9.668	0.662	10.207	78.95



Format	158.75x158.75mm±0.25mm
Thickness	190mm±30um
Front	9*0.1mm busbar(silver),114 fingers,blue silicon nitride anti-reflection coating(PID free)
Back	Back electrode width (silver) 1.8mm, back side cover aluminum back filed

Temperature Index	Intensity(W/m <sup>2</sup> )	Uoc	Isc
	<b>TkVoltage: -0.36 %/K</b>	1000	1.000
<b>TkCurrent: +0.07%/K</b>	900	0.996	0.903
<b>TkPower: -0.38%/K</b>	800	0.991	0.803
<b>Rsh≥30 Ω, Irev2≤0.8A</b>	600	0.988	0.602
	400	0.962	0.403



AOLI SOLAR WITH HIGH PERFORMANCE

[www.aolisolar.com](http://www.aolisolar.com)

Head Office:Rm 2506,Unit A ,Tianning Times Building,Changzhou City,JiangSu,China  
 Factory Add: C1 Buliding,Science & Technology Zone,Changzhou City,JiangSu,China  
 Email:info@aolisolar.com