


PIX ULTRA FAST CURE EVA FILM

PIX UFC



Solar EVA Sheet

ABOUT US

PIXON houses clean room and environment controlled facility up to 1 GW manufacturing line for EVA films.

PIXON Ultra Fast Cure EVA Films are specifically designed for enhancing the durability and increasing the performance of solar modules and are suitable for all types of Crystalline and Thin film PV modules with shorter cycling time that speeds up your module production with Excellent Transparency, High Reflectivity (Back side Film) increased Production Yield, Snail Trail Resistant, PID-Resistant, Lower Shrinkage, Excellent Performance with UV and Weather Stability.

PIXON EVA Film is proven for single stage as well as short cycle Multi Stage Lamination Processes.

CERTIFICATIONS



TUV tested - DH, EVA Thermal & Electrical Properties
TUV CTI Report : IEC 60112:2020



UL Certified
Certificate Number E526148

PIXON GREEN ENERGY PRIVATE LIMITED

1800 108 8800 | +91 281 6180000

sales@pixonenergy.com | www.pixonenergy.com

Regd. Office: 201-206, 2nd Floor, Star Avenue, Nr. Moti Tanki Chowk, Gymkhana Road, Rajkot - 360001. Gujarat, India.

Mfg Unit: Rajkot - Jamnagar Highway, PO: Depaliya, TA: Padadhari, Rajkot - 360110. Gujarat, India.



**Solar is
the New Green!**

TECHNICAL DATASHEET

PIX ULTRA FAST CURE EVA FILM



Technical Parameters For PIX UFC

| | Particulars | Test Method | Unit | Values |
|------------|----------------------------------|---------------------------|-------------------|---|
| Physical | Thickness | ASTM D 6988 | µm | ≥ 450 |
| | Width | Scale | mm | Up to 1335 (As per Customer Requirement) |
| | Melting Point | ISO 11357 | °C | 70 ± 3 |
| | GSM | ASTM D 6776 | g/m ² | 390 ± 20 |
| | Density | ASTM D 792 | g/cm ³ | 0.95 - 0.96 |
| | VA Content | 26 - 33 | % | 28 |
| Thermal | Melt Index (EVA – Glass) | ASTM D 903 | N/cm | ≥ 75 |
| | Water Absorption Test | ISO 62:200805 | % | < 0.1 |
| Electrical | Dielectric Strength | ASTM D 149 - 20 | kv/mm | > 25 |
| | Volume Resistivity | ASTM D 257 | Ohm.cm | ≥ 1x10 ¹⁵ |
| Optical | UV Cut Off | ASTM E 424 | nm | 360 ± 30 |
| | Transmittance | ASTM D 424 | % | ≥ 91 |
| | Refractive Index | ISO 489 | - | 1.48 |
| Mechanical | Peel Strength (EVA – Back Sheet) | ASTM D 903 | N/cm | ≥ 75 |
| | Tensile Strength | ASTM D 638 | MPa | 15 ± 3 |
| | Elongation | ASTM D 638 | % | ≥ 500 |
| | Shore hardness | ASTM D 2240 | SHORE-A | 70 ± 5 |
| Chemical | Gel Content | ASTM D 2765 / Oven Method | % | ≥ 75 |

| Lamination Properties | Lamination Parameter | Single Stage | Double Stage(Stage 1) | Double Stage(Stage 2) |
|-----------------------|----------------------|--------------|-----------------------|-----------------------|
| | Vacuum Time | 2 - 4 min | 2 - 4 min | - |
| | Lamination Time | 6 - 8 min | 1 - 2 min | 5 - 7 min |
| | Temperature | 140 - 150°C | 140 - 150°C | - |

*Laminator recipe depends on type of laminator.

- Temperature and Vacuum to be uniformly maintained across the laminator.
- Vacuum to be applied at -760 mm Hg, Periodic calibration of the machine input parameters to be done by Machine User.
- Lamination Parameters (cycle time) would vary from Laminator to Laminator also due to change in EVA/Module Width and Thickness of EVA, hence Extensive trials are suggested to get the desired results.


PACKAGING INFORMATION

Unless specified, below is the standard packaging data.

| | |
|----------------------------|------------------|
| Length/Roll | 140 or 150 metre |
| No. of Rolls/Pallet | 12 |
| Total Linear Metres/Pallet | 1680 or 1800 |
| Total SQM /Pallet | 1782 |

Each Roll is sealed in a protective bag in corrugated box | Boxes are strapped on suitable pallets with Protection Angle Board.

CHARACTERISTIC GRAPH



SPECTRAL TRANSMITTANCE

Storage Condition and Shelf Life: Store in undamaged original packaging, temperature between 20°C and 30°C and humidity between 50-60% RH. Recommended use within 9 months from date of manufacture.

- The above technical information represents the typical range of properties and is believed to be correct as on date.
- This data should however not be used to establish specification limits or used as basis for design.
- PIXON gives no warranty and assumes no liability in connection with any use of this information and is subject to the PIXON general terms and conditions.
- Lamination parameters and Quality of other components of the laminate during module manufacturing impact on the overall performance of the module, and hence we recommend the user to carry out intensive trials to test suitability of this product and module laminating conditions.