


ANDROMEDA 2.0

High Efficiency Series SPICN6(LAR)-60/IH

385W | 390W | 395W



FEATURES

- Up to 22.0% Efficiency
- IBC-No electrode to block sunlight
- N-Type cell has ZERO LID
- Excellent Temperature Coefficient
- Anti-PID
- Low mismatch loss
- Minimal power degradation (93% of initial after 25years)
- Double 25 Years Warranty



About SPIC


State Power Investment Corporation (SPIC)- FORTUNE GLOBAL 500 company ,one of the integrated energy group in China that holds assets of hydropower ,thermal power, nuclear power and new energy simultaneously . Hold and operate over 40GW photovoltaic projects, ranking first in the world (As of end 2021).



Electrical Parameters

Module Type	SPICN6(LAR)-60-385/IH		SPICN6(LAR)-60-390/IH		SPICN6(LAR)-60-395/IH	
	STC	NOCT	STC	NOCT	STC	NOCT
Maximum Power (Pmax/W)	385	290	390	294	395	298
Maximum Power Voltage (Vmpp/V)	35.5	32.9	35.7	33.1	35.9	33.3
Maximum Power Current (Impp/A)	10.85	8.82	10.93	8.89	11.01	8.95
Open Circuit Voltage (Voc/V)	41.8	40.0	41.9	40.1	42.0	40.2
Short Circuit Current (Isc/A)	11.72	9.42	11.83	9.49	11.94	9.57
Module Efficiency	21.5%		21.7%		22.0%	

Additional Value



Mechanical Parameters

Cell Type	N-IBC 166x83mm(Half-Cell)
No. of Cells	120(6x20)
Junction Box	Ip68 with three bypass diodes
Output Cable	4mm ² , 1200mm with MC4 (Length can be customized)
Glass	3.2mm coated tempered glass
Frame	Anodized aluminum alloy frame
Dimension	1727x1039x30mm
Weight	20.0kg


Operating Conditions

Maximum System Voltage	1500V DC(IEC)
Operational Temperature	-40~+85°C
Maximum Series Fuse Rating	20A
Mechanical Test Load (Front)	5400Pa
Mechanical Test Load (Rear)	2400Pa


Temperature Characteristics (STC)

Pmax	%/°C	-0.290
Voc	%/°C	-0.246
Isc	%/°C	+0.046

Dimensions(Units:mm)



I-V Curves(390W)



Packaging Configuration

No. of Modules Per Pallet	EA	35
No. of Pallets Per 40ft HQ container	EA	26
No. of Modules Per 40ft HQ container	EA	910



SPIC Solar Power Division
No.4 Jinggui Road, Chengdong District, Xining City,
Qinghai Province, China

en.spicsolar.com
spicsolar@spic.com.cn

Product specifications are subject to change without notice

© 2022 SPIC Solar Power Division. All rights reserved