



ESM190-156(60 cells) POLYCRYSTALLINE SOLAR MODULE



High module conversion efficiency, through superior manufacturing technology




Easy installation and handling for various applications



Entire module certified to withstand high wind loads (2400 Pa) and snow loads (5400 Pa)



ISO9001,OHSAS18001,ISO14001





An EverExceed high-power residential solar module is an aesthetic addition to most roofs

ENGINEERING EXCELLENCE

The perfect combination of high performance and design

ADVANCED AESTHETICS

Has an elegant appearance that blends beautifully with your home roof line

DURABLE

Provides long life and enhanced cell performance

HIGH PERFORMANCE

Uses advanced surface texturing to improve efficiency



EverExceed PV modules offer BTS-leading performance for a variety of applications

Power your application

When you choose EverExceed, you get more well-engineered products, you also get our proven reliability, outstanding customer service and the assurance of our 25-year limited warranty

www.everexceed.com

ESM190-156



190Watt


Electrical Characteristics

Type of Cell	Polycrystalline silicon
Cell Size(mm)	156mm
Module Efficiency	15.83%
Cell Configuration	60(6x10)
Size of module (mm)	1210x992x35mm
Weight per piece (Kg)	12.3Kg
Maximum power (Wp)	190W
Maximum power voltage (V)	31.5V
Maximum power current (A)	6.03A
Open circuit voltage (V)	38.0V
Short circuit current (A)	6.37A
Tolerance of Pmax	0~+5W

Standard Operating Conditions

Maximum system voltage (V)	1000V
Temperature coefficients of Isc (%)	0.053%/°C
Temperature coefficients of Voc (%)	-0.33%/°C
Temperature coefficients of Pm (%)	-0.42%/°C
NOCT (°C)	45°C±2°C
Temperature range	-40°C to +85°C
Surface maximum load capacity	60m/s (200kg/sq.m)
Series fuse rating	12A

Characteristics(Module I-V Graph 190W)



STC: Irradiance 1000W/m², Module temperature 25°C, AM1.5 spectrum.

Other Characteristics

Junction box type	Ip67 rated
Connectors and cables type	4mm ²
Length of cables (mm)	900mm
Frame (material, corners, etc.)	Anodized aluminum alloy
Glass	High transmissivity low-iron 3.2 mm toughened glass
FF (%)	≥78.55%

QUALIFICATIONS







10 years material and workmanship guarantee


95% power output guarantee for 5 years 90% power output guarantee for 10 years 80% power output guarantee for 25 years

EverExceed will not accept responsibility for damage caused to other equipment

Contact EverExceed to receive our latest product information

5 -year
95% power
10 -year
90% power
25 -year
80% power

Dimension



©Copyright 2018 EverExceed Corporation

www.everexceed.com